

GREY BOARD

TARGET CHARACTERISTICS								
PROPERTY	TOLERANCE	UNIT	GSM& STANDART	320	330	340	350	375
Gsm	%	g/m ²	ISO 536	320	330	340	350	375
Moisture	%	%	ISO 287	6,5	6,5	6,5	6,5	6,5
Bursting strength	Min.	kPa	ISO 2758	322	395	510	525	563
Burst index	Min.	kPa.m ² /g	ISO 2758	1,5	1,5	1,5	1,5	1,5
Internal Bond Strength	Min.	j/m ²	T 569 om-09	280	280	280	280	280

GUARENTEED CHARACTERISTIC								
PROPERTY	TOLERANCE	UNIT	GSM& STANDART	320	330	340	350	375
Gsm	±5%	g/m ²	ISO 536	320	330	340	350	375
Moisture	±3%	%	ISO 287	6,5	6,5	6,5	6,5	6,5
Bursting strength	Min.	kPa	ISO 2758	320	330	340	350	375
Burst index	Min.	kPa.m ² /g	ISO 2758	1,0	1,0	1,0	1,0	1,0
Internal Bond Strength	Min.	j/m ²	T 569 om-09	200	200	200	200	200

Reel Core ID: 100 mm