

HP FLUTING

TARGET CHARACTERISTICS										
PROPERTY	TOLERANCE	UNIT	GSM& STANDART	100	110	130	135	140	150	175
Gsm	Range	g/m ²	ISO 536	100	110	130	135	140	150	175
Moisture	Range	%	ISO 287	8	8	8	8	8	8	8
SCT CD	kN/m	kN/m	ISO 9895	1,9	2,1	2,4	2,5	2,6	2,8	3,3
SCT CD Index		kN.m/kg	ISO 9895	19	19	19	19	19	19	19

GUARANTEED CHARACTERISTICS										
PROPERTY	TOLERANCE	UNIT	GSM& STANDART	100	110	130	135	140	150	175
Gsm	±5%	g/m ²	ISO 536	100	110	130	135	140	150	175
Moisture	±3%	%	ISO 287	8	8	8	8	8	8	8
SCT CD	kN/m	ISO 9895	ISO 9895	1,7	1,9	2,2	2,3	2,4	2,6	3,0
SCT CD Index		kN.m/kg	ISO 9895	17	17	17	17	17	17	17