

MARKRAFT

| TARGET CHARACTERISTICS | | | | | | |
|------------------------|-----------|-----------------------|---------------|------------|------------|------------|
| PROPERTY | TOLERANCE | UNIT | GSM& STANDART | 110 | 130 | 150 |
| Gsm | % | g/m ² | ISO 536 | 110 | 130 | 150 |
| Moisture | % | % | ISO 287 | 8,5 | 8,5 | 8,5 |
| Bursting strength | Min. | kPa | ISO 2758 | 264 | 312 | 360 |
| Burst index | Min. | kPa.m ² /g | ISO 2758 | 2,40 | 2,40 | 2,40 |
| SCT CD | Min. | kN/m | ISO 9895 | 2,1 | 2,5 | 2,9 |
| SCT CD INDEX | | kN.m/kg | ISO 9895 | 19 | 19 | 19 |
| COBB ₆₀ TOP | Max. | g/m ² | ISO 535 | 35 | 35 | 35 |

| GUARANTEED CHARACTERISTICS | | | | | | |
|----------------------------|-----------|-----------------------|---------------|------------|------------|------------|
| PROPERTY | TOLERANCE | UNIT | GSM& STANDART | 110 | 130 | 150 |
| Gsm | ±5% | g/m ² | ISO 536 | 110 | 130 | 150 |
| Moisture | ±3% | % | ISO 287 | 8,5 | 8,5 | 8,5 |
| Bursting strength | Min. | kPa | ISO 2758 | 209 | 247 | 285 |
| Burst index | Min. | kPa.m ² /g | ISO 2758 | 1,9 | 1,9 | 1,9 |
| SCT CD | Min. | kN/m | ISO 9895 | 1,92 | 2,28 | 2,62 |
| SCT CD INDEX | Min. | kN.m/kg | ISO 9895 | 17,5 | 17,5 | 17,5 |
| COBB ₆₀ TOP | Max. | g/m ² | ISO 535 | 50 | 50 | 50 |

Date: 16.03.2023

KK-TS-014 Rev.01